



CI/SfB

(43)

V

JANUARY 2007
PRODUCT DATA SHEET

ARDEX DPM

Surface Damp Proof Membrane - Residual Moisture Suppressant

Features

Suppresses residual constructional moisture in cement/sand screeds and concrete floors

Can accommodate Hygrometer readings up to 98% RH

Guarantees the early laying of all floorcoverings

Easy to apply and fast curing

Available in two colours to allow the user to visually control coverage uniformity

Provides a sandwich damp proof membrane with ARDEX smoothing and levelling compounds

Provides a bonding agent for ARDEX A 35 rapid drying screeds

Can be used in conjunction with ARDEX Industrial Systems

Available in 3kg, 6kg and 25kg units



Reg No. FM 1207

ARDEX UK LIMITED
Homefield Road, Haverhill, Suffolk CB9 8QP UK.
Telephone: +44 (0)1440 714939
Fax: +44 (0)1440 716660
Technical Services Fax: +44 (0)1440 716640
Email: technical.services@ardex.co.uk
ARDEX online: www.ardex.co.uk

ARDEX DPM

Surface Damp Proof Membrane - Residual Moisture Suppressant

DESCRIPTION

ARDEX DPM is a solvent free, low viscosity, two component epoxy resin. After hardening the ARDEX DPM produces a membrane with high inherent strength and excellent bond strength to appropriate substrates including very damp concrete and screeds. ARDEX DPM accommodates hygrometer readings up to 98% RH.

ARDEX DPM has excellent resistance to water, grease, oil, aqueous salt solution, dilute mineral and organic acids and organic liquids and solutions.

ARDEX DPM is supplied in two colours, red for the first coat and green for the second coat, as a visual aid to application, thickness and coverage.

USE

ARDEX DPM has been specifically developed to suppress residual moisture in concrete and cement/sand screeded sub-floors and provides a surface damp proof membrane where a DPM is not present in the floor or it is not effective.

ARDEX DPM allows for the early installation of moisture sensitive floorcoverings/coatings in fast track building operations.

MOISTURE TESTING

This should be undertaken in accordance with BS 8203.

SUBSTRATE PREPARATION

The surface to be coated must be hard, sound and free of dust, laitance, dirt and other barrier materials such as paint, lime coatings, plaster and adhesive residues. Any existing screeds or levelling/smoothing compounds not resistant to moisture must also be removed.

Use ARDEX DGR degreaser to remove polish, wax, grease, oil and similar contaminating substances, followed by thorough mechanical preparation.

Concrete curing agents, admixtures and surface hardeners and the residues of these products can impair adhesion. Where doubt exists or the compatibility is unknown a trial adhesion test with the ARDEX DPM should be carried out before work commences. Please consult our Technical Services Department. Any incompatible curing agents, admixtures, surface hardeners or other surface contamination should be removed by scabbling, grinding, shot blasting or hot compressed air, as appropriate.

NOTE: ARDEX DPM must not be used over a sub-floor containing underfloor heating.

MOVEMENT JOINTS

Any joints or cracks in the floor subject to movement, such as structural movement joints, must not be bridged with the ARDEX DPM System. These joints must be treated with a flexible impervious jointing system and be carried through to the floor finish.

MIXING

In their original containers the resin and hardening agents are pre-gauged to the correct mixing ratio. The hardening agent (component B) is added to the resin (component A) and thoroughly mixed together with a spiral mixing paddle in a slow speed drill until a uniform colour and consistency is achieved. It is important that all the resin components have been mixed.

The ARDEX DPM is ready for immediate use and has a working time of 20 minutes at 20°C. This is reduced at higher temperatures and extended at lower temperatures. At higher temperatures it is recommended that the ARDEX DPM is spread out immediately after mixing as the reaction is exothermic and the heat generated in the container will reduce the working time. Apply at temperatures above 10°C.

NOTE: For the mixing instructions for the 25kg ARDEX DPM, please consult the packaging.

APPLICATION

Apply an even coat of the mixed ARDEX DPM by means of an appropriate notch trowel such as a 1.5mm x 5mm V shaped notched trowel. Whilst the ARDEX DPM

is still wet, the serration ridges should be flattened out with a long handled short pile paint roller, initially pre-wetted with the mixed ARDEX DPM. The thickness of application should not be less than 200 microns per coat, this can be checked using the ARDEX wet film thickness gauge. Coverage of 4m²/kg should not be exceeded.

NOTE: Coverage rates will be reduced by rough, porous substrates; pre-smoothing with ARDITEX, ARDITEX NA or ARDEX S 21 is recommended to aid application and improve yield.

NOTE: ARDITEX or ARDITEX NA should only be used if the DPM will be subsequently coated with ARDITEX or ARDITEX NA.

It is essential that the applied ARDEX DPM is continuous and free from pinholes or cavities, otherwise an additional application will be necessary. Allow to dry between coats. The second coat can usually be applied approximately 8 hours after the first one.

Latex Underlayment (ARDITEX / ARDITEX NA)

- 1 Apply an even continuous coat of mixed ARDEX DPM as per application instructions and allow to cure, usually 8 hours at 20°C.
- 2 Apply a second coat of ARDEX DPM as above, but at right angles to the first coat and allow to cure, usually 8 hours at 20°C.
- 3 Apply ARDITEX or ARDITEX NA smoothing compound to a minimum depth of 3mm, maximum 6mm to the cured ARDEX DPM and allow to dry.

Self-levelling Underlayment (ARDEX Underlayments)

- 1 Apply an even continuous coat of mixed ARDEX DPM as per application instructions and allow to cure, usually 8 hours at 20°C.
- 2 Apply a second coat of ARDEX DPM as above, but at right angles to the first coat and allow to cure, usually 8 hours at 20°C.
- 3 Prime the cured ARDEX DPM with ARDEX P 82 primer (consult Priming and Preparation data sheet) and allow to dry.
- 4 Apply the required ARDEX smoothing compound to a minimum depth of 3mm, maximum 6mm and allow to dry.

NOTE: If the existing sub-floor is not sufficiently smooth, pre-levelling can be undertaken with ARDITEX or ARDITEX NA smoothing compound when using ARDITEX, ARDITEX NA or ARDEX S 21 rapid hardening mortar when using ARDEX smoothing compounds.

Installing A Rapid Dry Screed With No Damp Proof Membrane

- 1 Mechanically prepare the concrete slab to expose a clean, sound surface.
- 2 Apply an even continuous coat of mixed ARDEX DPM as per application instructions and allow to cure, usually 8 hours at 20°C.
- 3 Apply a second coat of ARDEX DPM as above, but at right angles to the first coat and allow to cure.
- 4 Apply a third coat of ARDEX DPM and whilst still tacky, blind with 600 micron dry silica sand or ARDEX Fine Aggregate and allow to cure.
- 5 Apply a bonded ARDEX A 35 rapid setting, hardening and drying screed (consult the product data sheet).

NOTE: Apply sufficient sand to give a key free from resin. Remove excess sand by vacuum cleaner when cured.

COVERAGE

Approximately 4m²/kg e.g. one 6kg unit will cover approximately 24m² per coat at 200 microns.

PACKAGING

ARDEX DPM is supplied in pre-gauged metal duo containers. The hardener (component B) is in the small container and the resin (component A) is in the large container with room to mix in the hardener (component B) - net weight 6kg or 3kg.

25kg units of ARDEX DPM are supplied in pre-gauged plastic containers packed in a larger plastic mixing vessel.

STORAGE AND SHELF LIFE

Store in dry conditions. ARDEX DPM has a storage life of not less than 12 months in the original unopened containers.

CLEANING TOOLS

All tools should be cleaned, before the ARDEX DPM cures.

TECHNICAL DATA

Mixing ratio:	Component A: Component B 2:1 by weight.
Density at 20°C:	1.18
Working Time:	20 minutes at 20°C
Over Coating:	8 hours at 20°C
Walkability at 20°C	after 6-8 hours

PRECAUTIONS

The hardener which contains 4,4' - isopropylidenediphenol and amines classified as corrosive and the epoxy resin which contains bisphenol A/F-epichlorhydrin, can be irritating to the eyes and skin, and may cause sensitisation by contact.

They are considered harmful in contact with the skin and if swallowed. During mixing and application the following precautions should be observed: ensure adequate ventilation and avoid contact of the material with the eyes, nasal passages, mouth and unprotected skin.

Avoid contact with the hands by wearing protective gloves and by using, if necessary, a suitable barrier cream.

In case of contact with the eyes, rinse immediately with plenty of water and seek medical advice and after contact with the skin wash immediately with plenty of soap and water (do not use solvents). Prolonged contact with the skin should be avoided, especially where the user has an allergic reaction to epoxide materials. Always wear gloves and eye/face protection as necessary. Observe personal hygiene, particularly washing the hands after work has been completed or at any interruption whilst work is in progress. Care should be taken when removing gloves to avoid contaminating the insides.

In case of accidents seek medical advice.

Consult the relevant health and safety data sheets for full information.

NOTE: The information supplied in our literature or given by our employees is based upon extensive experience and, together with that supplied by our agents or distributors, is given in good faith in order to help you. Our Company policy is one of continuous Research and Development; we therefore reserve the right to update this information at any time without prior notice. We also guarantee the consistent high quality of our products; however, as we have no control over site conditions or the execution of the work, we accept no liability for any loss or damage which may arise as a result thereof.

Country specific recommendations, depending on local standards, codes of practice, building regulations or industry guidelines, may affect specific installation recommendations.