

## Heavy duty epoxy urethane joint sealant

### Uses

For sealing internal joints subject to heavy loading and abrasion, or where chemical resistance is required. Can be used in factories, warehouses and distribution centres. It is, particularly effective where there is forklift truck traffic. Nitoseal PU800 can also be used where joints would be subject to stiletto heels, shopping centres, podiums etc. It is suitable for use in prisons as an anti-pick sealant for sealing internal partitions, cell doors and windows, fittings and furniture.

### Advantages

- Cures to a tough seal
- Abrasion resistant
- High modulus
- Resistant to chemical, fuel and oil spillage
- Easily installed to give a flush finish
- Hard, but flexible sealant; resists picking and vandalism

### Description

Nitoseal PU800 is a two-component gun grade elastomeric sealant for limited movement joints. After mixing, the resultant compound will cure to provide an exceptionally robust seal, while retaining a degree of flexibility. Nitoseal PU800 is abrasion resistant and withstands spillage of fuel oils, mineral acids and vegetable oils. Nitoseal PU800 can be used in joints between 5 mm and 50 mm wide.

### Specification clauses

The joint sealant shall be Fosroc Nitoseal PU800, an epoxy urethane, heavy duty sealant. It shall be applied strictly in accordance with the Fosroc data sheet.

## Properties

### Nitoseal PU800

|   |   |
|---|---|
| Form:                                       | Two-part compound<br>Base: White paste<br>Curing agent: Grey paste  |
| Colour:                                     | Light grey  |
| MAF (BS 6093):                              | 10% for butt joints   |
| Cure:                                       | Chemical cure   |
| Pot life:                                   | 1 hour at 25°C  |
| Trafficking time:                           | 24 hours at 20°C: light traffic<br>48 hours at 20°C: heavy traffic  |
| Application temperature:                    | To avoid prolonged cure time apply Nitoseal PU800 above 5°C   |
| Hardness Shore 'A':                         | 65 to 80  |
| Chemical resistance to occasional spillage: | Resistant to alcohols, alkalis, mineral oil, hot detergent solution, 60% live steam, 25% mineral acids, vegetable oils and kerosene |
| UV resistance:                              | Some surface discolouration and slight surface hardening  |
| Solids content:                             | 100%  |
| Density:                                    | 1.4 g/cm <sup>3</sup>   |
| Flash point:                                | Over 65°C   |

## Application instructions

### Joint Design

Joints should be designed so that joint changes do not exceed the 10% MAF of Nitoseal PU800.

We would recommend that joints in new concrete slabs are left to the final stages of construction when temperatures have stabilised and the initial shrinkage has taken place.

Where joints are less than 25 mm and are fully supported by a solid backing, minimum depth should be 10 mm to 15 mm. Where a resilient filler provides the backing, the minimum depth should be 20mm. For wider joints a square section is preferable

# Fosroc® Nitoseal PU800

formerly Expoflex 800

## Preparation

Joint surfaces shall be clean, dry and free from contamination. Any voids or gaps at the base of the sealing slot should be filled and a suitable bond breaker should be pushed into construction and contraction joint slots. Where a particularly neat finish is required mask edges of joint before priming (if required) and sealant application.

## Priming

Where surface shall be subject to submersion or permanently damp, joints should be primed using Fosroc Primer MS2. Decant the entire contents of primer curing agent into the primer base tin and replace lid. Mix thoroughly by shaking tin for 2 minutes. Apply the primer using a clean dry paint brush working well in to ensure complete coverage. Nitoseal PU800 should be applied between 30 minutes and 4 hours after priming.

## Mixing

In cold weather Nitoseal PU800 mixes more easily if stored overnight at room temperature. Transfer the contents of the small tin into the base tin and mix thoroughly using a slow speed drill (300 to 500 rpm) fitted with a Fosroc Sealant Mixing Paddle until a uniform colour is achieved throughout. Immediately after mixing load the Nitoseal PU800 into a Fosroc "G" Gun using a follower plate. Extrude the sealant firmly into the joint to ensure complete contact with the joint face.

## Finishing

Nitoseal PU800 should be tooled off flush with adjacent surfaces. A minimum of surface lubrication such as dilute detergent solution may be used to assist the process. Remove masking immediately after tooling.

## Cleaning

Clean equipment immediately after use with Fosroc Equipment Cleaner.

## Estimating

Nitoseal PU800 is supplied in 2 litre tins in cartons of two.

### Guide to quantities

| Joint size<br>w x d in mm | Litres per<br>metre run | Metre run per<br>2.0 litre pack |
|---------------------------|-------------------------|---------------------------------|
| 5 x 15                    | 0.075                   | 26.67                           |
| 5 x 20                    | 0.100                   | 20.00                           |
| 20 x 10                   | 0.200                   | 10.00                           |
| 20 x 25                   | 0.500                   | 4.00                            |
| 25 x 25                   | 0.625                   | 3.20                            |
| 30 x 25                   | 0.750                   | 2.67                            |
| 30 x 30                   | 0.900                   | 2.22                            |
| 40 x 25                   | 1.000                   | 2.00                            |
| 40 x 40                   | 1.600                   | 1.25                            |
| 50 x 25                   | 1.250                   | 1.60                            |
| 50 x 50                   | 2.500                   | 0.80                            |

### Guide to Fosroc Primer MS2 coverage

| Joint depth | Metres of joint /750ml pack of primer |
|-------------|---------------------------------------|
| 10mm        | 500 - 600                             |
| 15mm        | 335 - 400                             |
| 20mm        | 250 - 300                             |
| 25mm        | 200 - 240                             |

Yields are theoretical, no allowance is made for substrate variation or wastage.

## Storage

Storage life Nitoseal PU800 18 months, Fosroc Primer MS2 18 months, in original containers and kept in dry conditions between 5°C and 27°C.

## Precautions

### Health and safety

For further information refer to appropriate Product Safety Data Sheet.

Fosroc and Nitoseal are trademarks of  
Fosroc International Limited



#### Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Services, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation, specification of information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation of information given by it.

## Fosroc Limited

Drayton Manor Business Park  
Coleshill Road, Tamworth,  
Staffordshire B78 3XN. UK

[www.fosroc.com](http://www.fosroc.com)

telephone:  
+44 (0) 1827 262222

fax:  
+44 (0) 1827 262444

email:  
enquiryuk@fosroc.com



Certificate number FM 610