

Renderoc SC

constructive solutions

Dry spray repair mortar

Uses

Renderoc SC is designed for large area repairs such as bridges, tunnels, retaining walls, dams, etc.

Advantages

- Low rebound
- Rapid strength gain
- Low water absorption and chloride ion diffusion
- Resistance to carbon dioxide penetration
- Excellent bond to the concrete substrate
- Single component — ready to use
- No added caustic accelerators
- Contains no chloride admixtures

Description

Renderoc SC is supplied as a ready to use blend of dry powders which is formulated for application using the dry spray process. The material is based on cements, with graded silica sands and silica fume.

Properties

The following results were obtained at a temperature of 20°C.

Test method	Typical result
Compressive strength at 20°C (BS 1881, Part 120: 1983):	1 day: 20 to 25 N/mm ² 7 days: 40 to 45 N/mm ² 28 days: 55 to 60 N/mm ²
Flexural strength (BS 1881, Part 118):	28 days: > 7 N/mm ²
Adhesion to concrete:	3 N/mm ²
Modulus of elasticity (BS 1881, Part 121):	> 25 KN/mm ²
Build —	
Vertical:	Up to 150 mm
Overhead:	Up to 90 mm
Minimum:	10 mm

Application instructions

Preparation

Clean the surface and remove any dust, unsound or contaminated material, plaster, oil, paint, grease, corrosion deposits or algae.

Where breaking out is not required, i.e. concrete is sound and of good quality, but cover is to be increased, roughen the surface and remove any laitance by light scabbling or abrasive-blasting. It will still be necessary to cut back the perimeter to a depth of 10 mm so that the repair patch may be 'toed-in' and finished flush with the surrounding concrete.

Oil and grease deposits should be removed by steam cleaning, detergent scrubbing or the use of a proprietary degreaser. The effectiveness of decontamination should then be assessed by a pull-off test.

Expose fully any corroded steel in the repair area and remove all loose scale and corrosion deposits. Steel should be cleaned to a bright condition paying particular attention to the back of exposed steel bars. Abrasive-blasting is recommended for this process.

Where corrosion has occurred due to the presence of chlorides, the steel should be high-pressure washed with clean water immediately after abrasive-blasting to remove corrosion products from pits and imperfections within its surface.

Reinforcing steel priming

Extra protection to the reinforcing steel can be achieved by application of one full coat of Nitoprime Zincrich Plus and allowing to dry before continuing.

Substrate priming

Soak the prepared concrete surface thoroughly, allowing surplus water to drain off.

Application

Exposed steel reinforcing bars should be firmly secured to avoid movement during the application process as this will affect mortar compaction, build and bond.

Renderoc SC should be emptied from the bags directly into the hopper of the dry spray process machine. The amount of water added should be controlled by the nozzleman. Too little water will increase rebound and dust emission, too wet a mix will slump.

If sagging occurs during application to vertical or overhead surfaces, the Renderoc SC should be completely removed and re-applied at a reduced thickness on to the correctly reprimed substrate.

Finishing

Renderoc SC is finished by striking off with a straight edge and closing with a steel float. Wooden or plastic floats, or damp sponges may be used to achieve the desired surface texture. The completed surface should not be overworked.

Low temperature working

Normal precautions for winter working with cementitious materials should then be adopted. The material should not be applied when the substrate and/or air temperature is 5°C and falling. At 5°C static temperature or at 5°C and rising, the application may proceed.

High temperature working

At ambient temperatures above 35°C, the material should be stored in the shade.

Renderoc SC

Curing

Renderoc SC is a cement-based mortar. In common with all cementitious materials, Renderoc SC must be cured immediately after finishing in accordance with good concrete practice, i.e. using wet hessian or polythene. In cold conditions, the finished repair must be protected from freezing.

Cleaning

Renderoc SC should be removed from tools, equipment and mixers with clean water immediately after use. Cured material can only be removed mechanically.

Equipment used with Nitoprime Zincrich Plus should be cleaned with Fosroc Solvent 102.

Limitations

Renderoc SC should not be used when the temperature is below 5°C and falling. The product should not be exposed to moving water during application. Exposure to heavy rainfall prior to the final set may result in surface scour. If any doubts arise concerning temperature or substrate conditions, consult the Customer Services Department.

Estimating

Supply

Renderoc SC:	25 kg bags
Nitoprime Zincrich Plus:	1.9 litre and 800 ml cans
Fosroc Solvent 102:	5 and 25 litre tins

Coverage and yield

Renderoc SC:	Approx. 12.5 litres / 25 kg bag (approx. 80 bags/m ³)
Nitoprime Zincrich Plus:	8 m ² /litre

Notes: The actual yield per bag of Renderoc SC will depend on the water addition during application. The coverage figures are theoretical — due to wastage factors and the variety and nature of possible substrates, practical coverage figures will be reduced.

Storage

Store in unopened bags in cool dry internal conditions. The product has a shelf life of 12 months from the date of manufacture if kept in dry storage in the original, unopened bags.

If stored at high temperatures and/or high humidity conditions the shelf life may be reduced to less than 6 months.

Precautions

Health and safety

For further information, refer to appropriate Product Safety Data Sheet.

Fire

Renderoc SC is non-flammable.

Nitoprime Zincrich Plus and Fosroc Solvent 102 are flammable. Keep away from sources of ignition. No Smoking. In the event of fire, extinguish with CO₂ or foam. Do not use a water jet.

Flash points

Nitoprime Zincrich Plus:	41°C
Fosroc Solvent 102:	33°C

For further information, refer to the Product Safety Data Sheet.



Fosroc Limited
Drayton Manor Business Park
Coleshill Road, Tamworth,
Staffordshire B78 3TL. UK

www.fosroc.com

Important note

Fosroc products are guaranteed against defective materials and manufacture and are sold subject to its standard Conditions for the Supply of Goods and Services, copies of which may be obtained on request. Whilst Fosroc endeavours to ensure that any advice, recommendation, specification of information it may give is accurate and correct, it cannot, because it has no direct or continuous control over where or how its products are applied, accept any liability either directly or indirectly arising from the use of its products, whether or not in accordance with any advice, specification, recommendation of information given by it.

Renderoc is the trade mark of Fosroc International Limited

telephone:
+44 (0) 1827 262222

fax:
+44 (0) 1827 262444

email:
uk@fosroc.com



Certificate number FM 610