

Sikadur®-30

Adhesive for bonding reinforcement

Product Description

Sikadur®-30 is a solvent-free, thixotropic, structural two part adhesive, based on a combination of epoxy resins and special filler, designed for use at normal temperatures between +8°C and +35°C.

Uses

Adhesive for bonding structural reinforcement, particularly in structural strengthening works. Including:

- Sika® CarboDur® Plates to concrete, brickwork and timber (for details see the Sika® CarboDur® Product Data Sheet).
- Steel plates to concrete (for details see the relevant Sika® Technical information).

Characteristics / Advantages

Sikadur®-30 has the following advantages:

- Easy to mix and apply.
- No primer needed.
- High creep resistance under permanent load.
- Very good adhesion to concrete, masonry, stonework, steel, cast iron, aluminium, timber and Sika® CarboDur® Plates.
- Hardening is not affected by high humidity.
- High strength adhesive.
- Thixotropic: non-sag in vertical and overhead applications.
- Solvent free.
- Hardens without shrinkage.
- Different coloured components (for mixing control).
- High initial and ultimate mechanical resistance.
- High abrasion and shock resistance.
- Impermeable to liquids and water vapour.

Tests

Approval / Standards

IBMB, TU Braunschweig, test report No. 1871/0054, 1994: Approval for Sikadur®-30 Epoxy adhesive.

IBMB, TU Braunschweig, test report No. 1734/6434, 1995: Testing for Sikadur®-41 Epoxy mortar in combination with Sikadur®-30 Epoxy adhesive for bonding of steel plates.



Product Data

Form

Colours	Part A:	white
	Part B:	black
	Parts A+B mixed:	light grey

Packaging	6 kg (A+B): pre-batched unit, pallets of 480 kg (80 x 6 kg). Not pre-dosed industrial packaging (pallets at 14 pails): Part A: 30 kg pails Part B: 10 kg pails
------------------	---

Storage

Storage Conditions / Shelf-Life	24 months from date of production if stored properly in original unopened, sealed and undamaged packaging in dry conditions at temperatures between +5°C and +30°C. Protect from direct sunlight.
--	---

Technical Data

Chemical Base	Epoxy resin.
----------------------	--------------

Density	1.65 kg/l \pm 0.1 kg/l (part A)	(at +23°C)
	1.65 kg/l \pm 0.1 kg/l (part B)	(at +23°C)
	1.65 kg/l \pm 0.1 kg/l (parts A+B mixed)	(at +23°C)

Sag Flow	On vertical surfaces it is non-sag up to 3-5 mm thickness at +35°C. (According to FIP (Fédération Internationale de la Précontrainte))
-----------------	---

Squeezability	4'000 mm ² at +15°C at 15 kg (According to FIP (Fédération Internationale de la Précontrainte))
----------------------	---

Layer Thickness	30 mm max. When using multiple units, one after the other. Do not mix the following unit until the previous one has been used in order to avoid a reduction in handling time.
------------------------	--

Change of Volume	Shrinkage: 0.04% (According to FIP (Fédération Internationale de la Précontrainte))
-------------------------	--

Thermal Expansion Coefficient	Coefficient W: 9 x 10 ⁻⁵ per °C (temp. range -10°C to +40°C)
--------------------------------------	--

Thermal Stability	Glass transition temperature: (According to FIP (Fédération Internationale de la Précontrainte))
--------------------------	---

Curing time	Temperature	TG
7 days	+45°C	+62°C

Heat deflection temperature: (According to ASTM-D 648)

Curing time	Temperature	HDT
3 hours	+80°C	+53°C
6 hours	+60°C	+53°C
7 days	+35°C	+53°C
7 days	+10°C	+36°C

Mechanical / Physical Properties

Compressive Strength

(According to EN 196)

Curing time	+10°C	+35°C
12 hours	-	80 - 90 N/mm ²
1 day	50 - 60 N/mm ²	85 - 95 N/mm ²
3 days	65 - 75 N/mm ²	85 - 95 N/mm ²
7 days	70 - 80 N/mm ²	85 - 95 N/mm ²

Shear Strength

(According to FIP (Fédération Internationale de la Précontrainte)):

Concrete failure (~ 15 N/mm²)

Curing time	+15°C	+35°C
1 day	3 - 5 N/mm ²	15 - 18 N/mm ²
3 days	13 - 16 N/mm ²	16 - 19 N/mm ²
7 days	14 - 17 N/mm ²	16 - 19 N/mm ²
14 days	15 - 18 N/mm ²	17 - 20 N/mm ²

Tensile Strength

(According to DIN 53455)

Curing time	+15°C	+35°C
1 day	18 - 21 N/mm ²	23 - 28 N/mm ²
3 days	21 - 24 N/mm ²	25 - 30 N/mm ²
7 days	24 - 27 N/mm ²	26 - 31 N/mm ²
14 days	25 - 28 N/mm ²	27 - 32 N/mm ²

Bond Strength

On steel > 21 N/mm² (mean values > 30 N/mm²) on correctly prepared substrate, ie. blastcleaned to Sa. 2.5

(According to DIN EN 24624)

On concrete: concrete failure (~ 4 N/mm²) on correctly prepared substrate

(According to FIP (Fédération Internationale de la Précontrainte))

E-Modulus

Static 12'800 N/mm²

(According to FIP (Fédération Internationale de la Précontrainte))

Strength Development

Confirm the strength development by producing cubes on site and testing them for compressive and flexural strength.

System Information

System Structure Sika® CarboDur® System:
For Application Details of Sika® CarboDur® Plates with Sikadur®-30, see the Sika® CarboDur® Product Data Sheet.

Application Details

Substrate Quality See the Product Data Sheet of Sika® CarboDur® Plates.

Substrate Preparation See the Product Data Sheet of Sika® CarboDur® Plates.

Application Conditions / Limitations

Substrate Temperature +8°C min. / +35°C max.

Ambient Temperature +8°C min. / +35°C max.

Material Temperature Sikadur®-30 must be applied at temperatures between +5°C and +30°C.

Substrate Humidity Max. 4% pbv
When applied to mat damp concrete, brush the adhesive well into the substrate.

Dew Point Beware of condensation!
Ambient temperature during application must be at least 3°C above dew point.

Application Instructions

Mixing Part A : part B = 3 : 1 by weight or volume
When using bulk material the exact mixing ratio must be safeguarded by accurately weighing and dosing each component.

Mixing Time



Pre-batched units:
Mix parts A+B together for at least 3 minutes with a mixing spindle attached to a slow speed electric drill (max. 600 rpm) until the material becomes smooth in consistency and a uniform grey colour. Avoid aeration while mixing. Then, pour the whole mix into a clean container and stir again for approx. 1 more minute at low speed to keep air entrapment at a minimum. Mix only that quantity which can be used within its potlife.

Bulk packing, not pre-batched:
First, stir each part thoroughly. Add the parts in the correct proportions into a suitable mixing pail and stir correctly using an electric low speed mixer as above for pre-batched units.

Application Method / Tools See the Product Data Sheet of Sika® CarboDur® Plates.

Cleaning of Tools Clean all tools and application equipment with Sika® Colma Cleaner/Thinner C immediately after use. Hardened / cured material can only be mechanically removed.

Potlife

(According to FIP (Fédération Internationale de la Précontrainte))

Temperature	+8°C	+20°C	+35°C
Potlife	~ 120 minutes	~ 90 minutes	~ 40 minutes
Open time	~ 150 minutes	~ 110 minutes	~ 30 minutes

The potlife begins when the resin and hardener are mixed. It is shorter at high temperatures and longer at low temperatures. The greater the quantity mixed, the shorter the potlife. To obtain longer workability at high temperatures, the mixed adhesive may be divided into portions. Another method is to chill parts A+B before mixing them (not below +5°C).

Value Base All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

Local Restrictions Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

Health and Safety Information For information and advice on the safe handling, storage and disposal of chemical products, users should refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

Legal Notes The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.



Sika Limited
Watchmead
Welwyn Garden City
Hertfordshire
AL7 1BQ
United Kingdom

Phone +44 1707 394444
Telefax +44 1707 329129
www.sika.co.uk, email: sales@uk.sika.com



ISO 14001 ISO 9001