

High-strength, chemically-resistant grout

weber.tec EP pourable grout

epoxy plus pourable grout



About this product

weber.tec EP pourable grout is specially formulated from epoxy resin and graded aggregates producing materials with exceptional toughness, chemical resistance, good flow characteristics and negligible shrinkage

Technical data

All tests carried out at 20°C.

| Strengths | | N/mm ² |
|-----------------------------------|--------|-------------------------------------|
| Compressive | 1 day | 52 |
| | 7 days | 70 |
| Flexural | 1 day | 25 |
| | 7 days | 35 |
| Tensile | 7 days | 16 |
| Tensile adhesion to abraded steel | 7 days | 14.5 |
| Flow (CEN 104-845-2) | | 55 mm |
| Flow (CEN flow trough) | | 240 mm in 30 sec. 380 mm finally |
| Effective bearing area | | > 90% |

Pot life or working time

Temperature

| | |
|-----------|-----------------|
| Below 5°C | Do not apply |
| 5°C | Approx. 5 hours |
| 10°C | Approx. 3 hours |
| 20°C | Approx. 1 hour |
| 35°C | 40 minutes |
| Over 40°C | Do not apply |

Uses

weber.tec EP pourable grout finds a wide application in the grouting-in of:

- Bearings
- Manhole frames
- Starter bars
- Dowels
- Balustrading
- Crane rails
- Machine baseplates
- Setting-in bolts
- Fixing runway lights
- Situations where tight clearances add to the difficulties of obtaining secure fixings

Features and benefits

- ▲ Capable of withstanding high dynamic loads
- ▲ High compressive and tensile strength
- ▲ Very good chemical resistance
- ▲ Cure within the temperature range 5°C to 35°C
- ▲ Negligible shrinkage factor allows use for underplate or rail grouting. Grout remains in contact with the underside
- ▲ Can be placed in much thinner sections than cementitious grouts resulting in cost savings

Chemical resistance

weber.tec EP pourable grout is shown to be unaffected by a wide range of acids, alkalis and industrial chemicals.

The results of immersion at 20°C to a typical range of chemical solutions and solvents are:

| | | |
|-------------------|-----|------------|
| Caustic Soda | 20% | Unaffected |
| Hydrochloric Acid | 20% | Unaffected |
| Sulphuric Acid | 20% | Unaffected |
| Detergent | | Unaffected |
| Petrol and Oil | | Unaffected |

weber.tec EP pourable grout

Preparation

Concrete surface

Concrete must be suitably prepared by scabbling, needle gunning or grit blasting to remove all cement laitance, grease, oil and other contaminants. The surface should be roughened to provide a bond and have a minimum surface texture of ± 1 mm. Wet surfaces should be dried by using a hot, compressed-air lance. The advantages of this are: it dries the surfaces of both the concrete and the steel, it warms up the surfaces of concrete and steel, allowing the grout to flow better in colder conditions. It also ensures better drying under the plate.

Steel plate

Bearing plates must be degreased with a suitable solvent such as methyl alcohol, acetone etc. The adhesive bond to grit-blasted steel is in excess of 10 MPa. This bond is reduced by coatings or galvanising on the steel plate; this will depend on the bond of the applied coating to the steel and the bond of the coating to the resin grout. Plug any holes in the steel plate and apply grease or silicone wax to any removable bolts and nuts.

Shutter design

Place and fix greased shuttering around the plate. There should be no gaps at the sides, just one at each end, one for air release (5 mm to 10 mm) and the other for grout filling (min. 25 mm). The hopper providing the pressure head must be at least 100 mm high. Normal ratio is 1:3 (height of hopper: length of pour).

To reduce wastage, construct a moveable hopper that can be shut off and placed over the next filling gap. This hopper can be made of thin steel sheet or aluminium and should have handles on the side. The bottom should be at least 25 mm wide and the top of the hopper should be about 75 mm wide to aid pouring.

Mixing

A forced-action mixer such as a Mixal or Creteangle is recommended. Alternatively, use a powerful drill (> 800 W) at a slow rotational speed (< 400 rpm) with a Refina MR4 mixing blade, which improves mixing efficiency of resin mixtures.

Use a mixing bucket of capacity 20 litres with a diameter of about 20 – 25 cm.

Pour the contents of the bottle of hardener into a suitable bucket and add the contents of one can of resin. Mix for at least 30 seconds then add one full bag of powder gradually while continuing to mix for 1 minute. Ensure that the mixing blade is below the grout level at all times and has fully mixed all the contents especially at the bottom of the bucket. The mixed material must be uniform in colour, indicating that the components are fully blended.

It is important to keep the mixing head below the level of the grout during mixing to avoid entrapment of air.

For sections thicker than 50 mm, the addition of up to 12.5 kg of dry, single-sized pea gravel (5mm) per 25 kg mix is permitted.

Application

Pouring

Immediately after mixing, pour the mixed grout into place, using a spatula to aid transfer of contents if necessary.

It is imperative that a hopper is used to help the grout to flow quickly. Removable hoppers with valves are recommended. As soon as the grout has reached and has filled the small air slit at the opposite end of the shutter, close off the valve in the hopper and move the hopper to the next plate. Remove excess grout and any grout that has spilled onto the plate with a palette knife or scraper.

Pumping

Pumping is best using a peristaltic pump. **Weber** can recommend suitable machinery.

When pumping, place the end of the hose under the centre of the plate so the grout radiates from the centre. When the grout has reached the far side, start to withdraw the hose very slowly with the pump running to avoid forming air pockets.

Protection

The completed grouted plates must be protected from rain, strong sun and frost for a minimum period of 24 hours during cure.

Cleaning

Fresh grout that has not yet set can be removed with **weber.tec solvent 3** using a cloth or brush to clean tools and spillages.

Set grout has to be removed with methylene chloride paint stripper and care must be taken during its use.

Packaging and yield

weber.tec EP pourable grout suitable for gap sizes 5 – 75 mm:

A three-component pack which makes up into one mix.
Pack size 25 kg – yield approx. 14 litres.

Storage and shelf life

The shelf life of **weber.tec EP pourable grout** is in excess of 12 months if stored in cool, dry, frost-free conditions.

Health and safety

Contains epoxy constituents. Refer to information supplied by manufacturer (see Material Safety Data Sheet).

All skin contact with epoxy resin products should be avoided. Barrier creams should be used and operatives should wear protective clothing including gloves. Working areas should be well ventilated.

The hardener content is alkaline and labelled as corrosive. The resin content is labelled as an irritant. The flash point of all components is in excess of 100°C. In the event of fire use foam, dry chemical, carbon dioxide (CO₂) or water fog extinguishers.

For further information, please request the Material Safety Data Sheet for this product.

Technical services

Weber's Customer Services Department has a team of experienced advisors available to provide on-site advice both at the specification stage and during application. Detailed specifications can be provided for specific projects or more general works. Site visits and on-site demonstrations can be arranged on request.

Technical helpline
Tel: (01525) 722110

Sales enquiries

Weber products are distributed throughout the UK through selected stockists and distributors. For UK sales enquiries and overseas projects, contact **Weber's** Sales office.

Sales office
Tel: (01525) 722100
Fax: (01525) 718988

Saint-Gobain Weber Ltd

Dickens House, Enterprise Way, Maulden Road, Flitwick, Bedford MK45 5BY, UK
Tel: 08703 330070 Fax: (01525) 718988 e-mail: mail@weberbuildingsolutions.co.uk

To the best of our knowledge and belief, this information is true and accurate, but as conditions of use and any labour involved are beyond our control, the end user must satisfy himself by prior testing that the product is suitable for his specific application, and no responsibility can be accepted, or any warranty given by our Representatives, Agents or Distributors. Products are sold subject to our Standard Conditions of Sale and the end user should ensure that he has consulted our latest literature.