

DATA Sheet



FASTFILL WP

USES

Rapid setting, polymer modified cementitious mortar for arresting water seepage and infiltration under pressure through cracks, joints and voids in concrete and masonry. Can also be used for rapid sealing and jointing in and around pipework or in water retaining structures.

ADVANTAGES

USER FRIENDLY:	Materials are pre-packaged and only require mixing with clean water on-site.
NON-SHRINK:	Maintains high bond strength to substrate and ensures a durable watertight seal.
RAPID SETTING:	Sets in 2 minutes at 20°C, yielding a durable, high strength mortar.
COMPATIBLE:	Physical properties of cured materials similar to base concrete.
POLYMER MODIFIED:	Ensures enhanced adhesion in jointing situations and prevents wash-out.
SAFE:	Non-toxic when cured.

PRODUCT DESCRIPTION

FASTFILL WP is a single component, polymer modified, fibre reinforced, Portland cement based plugging and sealing compound. When mixed with water it exhibits unique hydraulic properties to produce a rapid setting mortar which can arrest water seepage and infiltration through joints, cracks or porous areas in concrete and masonry structures. It is ideally suited for sealing in and around pipework and for forming fillets in tanking situations.

TECHNICAL DATA

Mixed Colour:	Concrete Grey.
Mixed Density:	2150kg/m ³ .
Min. Application Thickness:	20mm.
Min. Application Temperature:	5°C.
Max. Application Temperature:	25°C.
Final setting time:	2-3minutes at 20°C.

MECHANICAL CHARACTERISTICS (TYPICAL)

Compressive Strength: BS 4551 Tested at 20°C:

Age	N/mm ²
1 Hour	10.0.
2 Hours	16.5.
4 Hours	25.0.
1 Day	34.5.
7 Days	45.0.
28 Days	66.0.

APPLICATION DATA

Application Guide available on request.

PREPARATION

Mechanically remove all damaged concrete and masonry back to a sound core. Joints and cracks should be square cut or ideally dovetail cut out to a minimum depth and width of 20mm. On cutting back, feather edges and V-cuts must be avoided. The perimeter of the area should be stepped to a depth of 10mm by means of saw, disc cutting or preferably using a power chisel.

The areas to be treated must be free from all unsound material, i.e. dust, oil, grease, corrosion by-products and organic growth. Smooth surfaces should be roughened, all loose material and surface laitance removed using high pressure water techniques.

The prepared substrate should be thoroughly soaked with clean water until uniformly saturated without any standing water.

MIXING

FASTFILL WP should be mixed by hand in a clean plastic or rubber bowl. Ideally no more than 0.5kg should be mixed at a time using an initial mix ratio by volume of 1 part of water to 3-4 parts of **FASTFILL WP**. Adjust the mix ratio as necessary to give a putty like consistency. Mixing time must not exceed 2 minutes.

PLACING

The mixed material should be formed into a ball shape in a gloved hand until slight stiffening occurs. The **FASTFILL WP** should then be forced into the void with a minimum of working and held in place firmly for 1-2 minutes until setting occurs.

When sealing joints in pipework or forming a fillet at a wall/floor angle, a steel float or coving trowel may be used to produce the desired finish.

CURING

Once the **FASTFILL WP** has been placed and stiffened sufficiently, the surface should be kept in a damp condition for a minimum of 15 minutes to aid curing.

CLEANING

All tools should be cleaned with water immediately after use.

SHELF LIFE

12 months in dry, frost free conditions with unopened containers at 20°C.

PACKAGING AND COVERAGE

Pack Size: 8kg.
Yield: One 8kg pack yields 4.25 litres of mortar.
Coverage: 2.15kg/mm/m².

SAFETY DATA

Safety Data Sheet available on request.

12/06



Flexcrete Technologies Limited

Tomlinson Road • Leyland • Lancashire
• PR25 2DY • England

Tel: +44 (0) 845 260 7005 • **Fax:** +44 (0) 845 260 7006

e-mail: info@flexcrete.com

www.flexcrete.com

