

Aidol® DUR AQUA HARDENER



Article No. 3806

Hardener component for Aidol dur Aqua Varnishes

Range of use:

By adding the hardener to the following products:
Aidol dur Aqua Universal Varnish
Aidol dur Aqua Color
Aidol dur Aqua Stairs Varnish
Aidol dur Aqua Filler
the quality of the varnish film is considerably improved

Working:

Mixing ratio 10:1 (varnish:hardener)
The hardener must be worked into the varnish with a dissolver.
The original viscosity is achieved again by adding approx. 10% water.

Notes:

Close containers tightly after use.

Tools and cleaning:

Clean tools immediately after use with water and a detergent.
Dispose of the remains from cleaning properly.

Application rate:

10% of the products listed above.

Shelf-life:

At least 6 months stored dry and frost-free in original containers.

Characteristic data of the product:

Density:	1.10 g/m ³ at 20°C
Viscosity:	950 mPa s at +20°C
Binder:	polyisocyanate
Solid content:	78%
Flash point:	98°C
Packaging:	0.5 l, 2 l and 20 l tin cans

Safety data:

This product contains aliphatic polyisocyanate. Observe the notes provided by the producer.

Danger warning:
Skin contact may cause sensitisation.

Safety advice:
Keep out of reach of children.
Avoid contact with skin and eyes.
Wear suitable protective gloves when working.
Use only in well ventilated areas.

Disposal:

Dispose of product remains according to valid regulations.
Completely empty cans may be recycled.

Ecology:

Do not lead into bodies of water, the sewer system or the ground. Water hazard class 2.

Labelling:

Regulations on flammability:	-/-
Regulations on hazardous substances	Xi irritating
GGVS/ADR	-/-

Safety, ecology, disposal:

Further information concerning safety during transport, storage and handling as well as for disposal is found in the latest Safety Data Sheet.

The statements above are compiled from our field of production and according to the latest technological developments and application techniques. Since application and working are beyond our control, no liability of the producer can be derived from the contents of this information sheet.

Any statements made beyond the contents of this information must be confirmed in writing by the producer.

In all cases, our general conditions of sale are valid.

With the publication of this Technical Information Sheet all previous editions are no longer valid.