

Technical Information Sheet
Article No. 9944

PUR Color Top CPD

2-component solvented polyurethane coating

Typical Installations

- As a seal coat on car park deck coatings.
- As a seal coat on balcony waterproofing systems.

Characteristic data of the product

Intercoat times @ 20°C	16 – 24 hours
Pot Life @ 20°C:	40 minutes
Appearance:	Coloured
Density:	1.2 g/cm ³
Solids Content:	~ 70 %
Full cure @ 20°C:	5 days

Avoid the `dew point`

Property Profile

Solvent containing 2-component coating on a polyurethane base. Top coating and seal coat for elastic waterproofing systems in car parks and balconies.

Range of Use

As a seal coat over Remmers PUR Indu Color. Take care not to exceed 0.5 kg/m²/coat. Max. aggregate size should be 0.7 mm to avoid over-application of the coating.

Substrates

All surfaces prepared according to Technical Information Sheet for a suitable primer, i.e. Epoxy FAS 100, Epoxy ST 100, Epoxy MT 100 etc. See Technical Data Sheet of the primer for minimum and maximum time between application steps. On blinded substrates, the coating may even be applied after some days.

System Components

- Primer: Epoxy FAS 100
Art. No. 0916
0.3 – 0.5 kg/m²
- Base: PUR Uni Color BC
Art. No. 9941
1.0 kg/m²
- Top: PUR Indu Color TC
Art. No. 9942
0.7 kg/m²
- Broadcast: Quartz 02/07
Art. No. 4417
3 - 4 kg/m²
- Sealer: PUR Color Top CPD
Art. No. 9944
0.5 kg/m²

Directions:

Add the hardener to the basic compound and mix thoroughly with a slow speed mixer (max. 400 rpm). Pour the mixture into a separate container and mix again.

Insufficient mixing leads to the formation of blisters and causes soft, incompletely cured spots.

Guidelines for working:

The temperature of the material, surrounding air and substrate must be at least 8 °C, max. 30 °C. Relative humidity may not exceed 80%. The temperature of the substrate must be at least 3 °C above the dew point temperature.

Notes:

Because of raw material composition, slight colour difference between different batches may occur. Hence, use drums of the same batch for application on larger surfaces only.

Tools and cleaning:

Suitable tools like smoothing trowel, notched trowel, blade, roller mixing equipment to the counter-current principle.

Clean tools, equipment and any spilled material immediately while fresh with V 101. After hardening, the product may only be removed mechanically.

Packaging and storing:

Shelf-life:

At least 12 months in closed and unmixed, original containers stored frost-free.

Safety, ecology, disposal

Further information on safety when transporting, storing and handling as well as disposal and ecology are found in the latest Safety Data Sheet.

The statements above are compiled from our field of production and according to the latest technological developments and application techniques.

Since application and working are beyond our control, no liability of the producer can be derived from the contents of this information sheet. Any statements made beyond the contents of this information must be confirmed in writing by the producer.

In all cases, our general conditions of sale are valid. With the publication of this Technical Information Sheet all previous editions are no longer valid.

9944-TI-05.07



Remmers (UK) Limited Crawley
United Kingdom
Tel: +44(0) 845 373 0103
Fax: +44(0)845 373 0104
www.remmers.co.uk

Remmers (Far East) Pte. Ltd.
Singapore
Tel: +65 6 7410277
Fax: +65 6 7417158