

Technical Information Sheet  
Article No. 222020, 222023,  
222025, 222028

## Arte Mundit

Peeling cleaning agent

Type I Art. No. 222020

Type II Art. No. 222023

Type III Art. No. 222025

Type V Art. No. 222028

### Range of use

Arte Mundit is a self-vulcanising cleaning paste for thorough, water-free removal of dust, soot, nicotine residue and other soiling on interior walls, ceilings, floors, stucco, natural stone, marble, concrete, brick, render, gypsum sculptures, polished wood, synthetic materials, etc.

### Property profile

Arte Mundit is an environmentally correct cleaning paste on a natural raw material base. The fresh product vulcanises by drying into an elastic rubber with good soil binding capacity. Arte Mundit does not contain any organic solvents, surface active agents or inorganic salts.

The A-components in the Arte Mundit programme differ in their reactivity and compatibility with auxiliary agents. Arte Mundit Type I is a modified latex emulsion that is always used without an additive. After activation with the B-component, Arte Mundit Types II, III and V contain varying concentrations of complexing agents and cleaning intensifiers that either volatilize during vulcanisation or are bound into the dry film.

A contamination of the substrate with these substances is therefore not possible.

### Characteristic data of the product

Density of A-components:	0.94 g/ml
Density of B-components:	0.99 g/ml
pH value of A-components:	9.0 (10% in water)
pH value of B-components:	10.0 (10% in water)

#### Typical vulcanisation times:

20 °C - 40% relative humidity	approx. 3 hours
20 °C - 65% relative humidity	approx. 3 hours
20 °C - 95% relative humidity	approx. 22 hours

5 °C - 65% relative humidity	approx. 23 hours
10 °C - 65% relative humidity	approx. 22 hours
20 °C - 65% relative humidity	approx. 3 hours
30 °C - 65% relative humidity	approx. 2.5 hours

### Directions

All surfaces that are not to be treated, varnished areas, sensitive metals, etc. should be carefully covered with PE sheets before work with Arte Mundit begins. The substrate to be cleaned must be dry and free of dust and loose deposits.

Stir Arte Mundit well, add the B-component if required, mix thoroughly and then apply to the substrate which has been coarsely cleaned with a brush, using a suitable tool and covering the entire surface. Fill undercut areas and contours thoroughly with Arte Mundit.

After thorough drying, the film is removed by carefully pulling it off (e.g. from the top left towards the bottom right), keeping tensile force as constant as possible. This is carried out in general approx. 24 hours after application. Avoid waiting times that are longer (more than 3 days) since the elasticity of the film is lost, making it much more difficult to pull off. When Arte Mundit Type I is used, the surfaces do not need to be washed off afterward.

Surfaces treated with the activated Types II, III and V are cleaned again after the vulcanised material has been pulled off by wiping off

with a sponge dampened with just a little clear water, starting at the highest point. If necessary, a medium-hard nylon brush can be used for somewhat more intensive cleaning.  
Use as little water as possible.

### Notes

An introduction to working with Arte Mundit should be given before work is started.

The specific mixing ratios (for Types II, III and V) must be strictly observed.

The selection of the type of Arte Mundit to be used depends on the condition of the substrate, type and intensity of soil and desired cleaning result. Before working with airless equipment (e.g. made by Wagner), please get in touch with us.

Do not use on hot substrates.

### Tools

Brush, lambskin roller, filling knife and smoothing trowel  
We recommend the use of stainless steel or plastic tools.

### Application rate, packaging, shelf-life

#### Application rate:

Approx. 0.7 - 1.0 kg/m<sup>2</sup> on smooth surfaces

Up to approx. 3.0 kg/m<sup>2</sup> on textured surfaces

#### Packaging:

A-component: **PE bucket**

B-component: **tin bucket**

#### Type I

A-component: 15 kg

#### Type II

A-component: 15.00 kg

B-component: 1.01 kg

#### Type III

A-component: 15.00 kg

B-component: 2.86 kg

#### Type V

A-component: 15.00 kg

B-component: 3.84 kg

#### Shelf-life:

Max. 12 months stored dry and frost-free in original containers.

### Safety, ecology, disposal

Further information on safety when transporting, storing and handling as well as disposal and ecology is found in the latest Safety Data Sheet.

The statements above are compiled from our field of production and according to the latest technological developments and application techniques.

Since application and working are beyond our control, no liability of the producer can be derived from the contents of this information sheet. Any statements made beyond the contents of this information must be confirmed in writing by the producer.

In all cases, our general conditions of sale are valid. With the publication of this Technical Information Sheet all previous editions are no longer valid.

Remmers India Pvt. Ltd.  
Gurgaon  
Tel.: +91 124 400 9131  
Fax: +91 124 400 9134  
www.remmers.in



Remmers (UK) Limited Crawley  
United Kingdom  
Tel: +44(0) 845 373 0103  
Fax: +44(0)845 373 0104  
www.remmers.co.uk

Remmers (Far East) Pte. Ltd.  
Singapore  
Tel: +65 6 7410277  
Fax: +65 6 7417158