

Adesso APP



Product Data Sheet

Polyester based polymer modified torch-on cap sheets

April 2007

Features and Benefits:-

- Torch-on application
- High softening point coating
- Strong glass fibre reinforced polyester base
- Durable APP modified bitumen
- Low temperature flexibility -5°C
- Cost effective performance
- 10 year material guarantee

Description

Adesso APP torch-on is a limited range of polyester based, slate surfaced torch-on cap sheets, coated with a high softening point APP modified bitumen coating. The embossed backing helps rapid dispersion of the torching film, making application fast and secure.

Adesso APP torch-on membranes provide reliable and effective flat roof waterproofing, combining the qualities of excellent performance, good handling characteristics and economy. They can be applied onto suitable pour and roll or torch-on underlays as part of a built-up system, or as a refurbishment overlay to existing asphalt or selected mineral surface bitumen membranes. (NB. For a list of suitable torch-on underlays see separate APP Underlays data sheet.)

Dimensions & Weights	Adesso APP Torch-On Slate
Roll Weight kg	34
Weight kg/m ²	4.3
Roll Length m	8
Roll Width m	1
Selvedge Width mm	75
Product Components	
Base	Glass Fibre/Polyester
Typical Performance	
Tensile Strength (MD) N/50mm	400
Tensile Strength (TD) N/50mm (Moat 27: 6C: 1984)	300
Elongation (MD) %	20
Elongation (TD) % (Moat 27: 6C: 1984)	30
Low Temperature Flex $^{\circ}\text{C}$ (Moat 27: 6D: 1984)	-5

Product Codes:	
Adesso Green Slate	72175302
Adesso Brown	72175304
Adesso Black	72175301

Product Details

Adesso APP Slate Surfaced

Cap sheet - Utilises a glass fibre reinforced polyester base, coated with APP modified bitumen, providing a very high degree of strength and durability. Available with a green, brown or black slate finish and surfaced on the underside with flame dispersible polyethylene. For exposed use and needing no further finishing on site.

Application

Adesso APP torch-on can be used as the cap sheet onto suitable pour and roll or torch-on underlays as part of a built-up system or as refurbishment overlay to existing asphalt or selected mineral surface felt. When installing a fully torched system, suitable underlays include Universal Torch Underlay.

Adesso APP torch-on roofing membranes should be installed in accordance with BS 8217: 2005, Code of Practice for Reinforced bitumen membranes for roofing, and to IKO PLC specifications. The application should follow the recommended good practices for torch-applied membranes. Care must be taken when applying Adesso APP torch-on membranes in close proximity to combustible materials, decorative coatings and heat sensitive materials.

Apply Adesso APP torch-on roofing by melting the heat dispersible backing and coating to create a molten flow in front of the roll. The flame of the torch should be applied at the low point where the roll meets the underlay. As the film and bitumen melts, roll the roofing forward. Side joints in the sheets should be fully bonded and formed using the 75mm selvedge. NB. A bead of bitumen must exude from all lap joints to ensure a seal.

Other products

Full product literature, health & safety and technical sheets are available as downloads from our website www.ikogroup.co.uk or on request by email: marketing@ikogroup.co.uk

IKO PLC

Literature Enquiries

E-Mail: marketing@ikogroup.co.uk Website: www.ikogroup.co.uk

Customer Services

Appley Lane North, Appley Bridge, Wigan, Lancashire WN6 9AB
Tel: 0800 028 5573 Fax: 0800 013 5574 E-Mail: sales@ikogroup.co.uk

Technical & Design Services

Coney Green Road, Clay Cross, Chesterfield, S45 9HZ
Tel: 0844 412 7228 Fax: 0844 412 7229 E-Mail: technical@ikogroup.co.uk

Whilst every care is taken to see that the information given in this literature is correct and up to date it is not intended to form part of any contract or give rise to any collateral liability, which is hereby specifically excluded. Intending purchasers of our materials should therefore verify with the company whether any changes in our specification or application details or otherwise have taken place since this literature was issued.