



Rugasol® C/MH+

Concrete Surface Retarders

Technical Data Sheet

DESCRIPTION

Rugasol surface retarders have been specially designed for producing a mechanical key to construction joints, stop ends, or subsequent rendering applications. **Rugasol** is normally supplied in two standard grades.

- i) **Rugasol MH+** – water based gel-retarder for on site exposed aggregate work.
- i) **Rugasol C** – liquid retarder for horizontal construction joints and surfaces.

Rugasol products will only delay the ultimate hardening and does not “kill” the set of the cement. When used correctly **Rugasol** will not stain concrete, even white concrete. **Rugasol** will not affect the bond of reinforcement to concrete, if accidental splashing occurs it should be thoroughly cleaned with clean water.

USES

- * **Rugasol MH+** provides an efficient, economical method of obtaining a rough bonding surface without the need for hacking, chipping or sand-blasting.
- * **Rugasol MH+** is painted directly on formwork for walls, ceilings, vertical construction joints or any similar formed concrete surface.
- * **Rugasol MH+** dries on the formwork to a tough, water and abrasion resistant film. It is not affected by light foot traffic or by light showers. Forms may be coated before or after erection. Reinforcing steel is placed as usual.
- * **Rugasol MH+** will retard the set of the cement paste by up to 6 mm ($\frac{1}{4}$ ") depth, the depth depends upon the thickness of the coating, the time elapsed before the retarder is removed, the cement content of the concrete and the quantity of water in the mix. The ambient temperature will also affect the depth of retardation.

ADVANTAGES

- * **Rugasol MH+** is a red gel, which is ready for use from the container. It should be stirred before use and must not be diluted.
- * **Rugasol MH+** may be applied to any type of clean form. Apply a heavy coat with a brush or roller and allow to dry (normally 2 to 4 hours). A waiting time of up to 3 days may be permitted prior to placing concrete. Protect surfaces from rain etc during waiting time. Brushes and equipment can be cleaned before the material hardens, using water. No mould oils should be on the forms. Coated surfaces should be protected from strong sunlight.

Technical Data (typical)

Form: C – Liquid MH+ – Gel
Colour: C – Green MH+ – Pink

All above values are approximate.

METHOD OF USE

USES – Rugasol C

Rugasol C is an easy and economical method of obtaining a mechanical key for 'kicker' joints, renderings and screeds on horizontal surfaces of freshly placed concrete.

Rugasol C eliminates the need for sandblasting, hacking and bush hammering leaving the aggregate unbroken and firmly embedded.

DISPENSING

Approximately 5–10 sq metres per litre.

IMPORTANT NOTES

Rugasol C is a green water like liquid that is ready to use straight from the container. It should be sprayed onto the horizontal concrete surface as soon as the initial 'bleeding' of the concrete has finished. (A large garden spray or watering can is quite suitable.) After the initial cure of the concrete has elapsed, the soft cement paste on the surface can be brushed off the exposed aggregate finish finally washed down with clean water. White **Rugasol C** is in use the concrete surface must be protected from rain, dirt etc.

The depth of exposure can vary for different mix designs; however, a depth of up to 4mm is normal. Spray equipment should be washed out after use with hot water.

Keep containers closed when not in use and out of the reach of children. Do not transfer **Rugasol C** into unlabelled containers.

The retarding compound in **Rugasol C** combines with cement at the surface and delays the normal hydration for approximately 1–2 days (high cement contents and temperatures will reduce the retardation). After this retardation has finished, the concrete cures to its full strength.

PACKAGING

Refer to latest price list

STORAGE AND SHELF LIFE

Minimum 1 year in sealed containers stored in dry warehouse condition (+5°C – +25°C). Protect from frost.

Handling Precautions

Sika products are generally harmless provided that certain precautions normally taken when handling chemicals are observed. The materials must not, for instance, be allowed to come in contact with foodstuffs or food utensils and measures should also be taken to prevent the uncured materials from coming in contact with the skin, since people with particularly sensitive skin may be affected. The use of protective clothing, goggles, barrier creams and rubber gloves is required. The skin should be thoroughly cleaned at the end of each working period either by washing with soap and warm water or by using a resin-removing cream - the use of powerful solvents is to be avoided. Disposable paper towels - not cloth towels - should be used to dry the skin. Adequate ventilation of the working area is recommended. In case of accidental eye or mouth contact, flush with water - consult a doctor immediately. Health and Safety information on Sika Products is available and we strongly advise that this is read prior to their use. Sika products are for professional use and should be stored in sealed containers away from the reach of children.

Important Note

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users should always refer to the most recent issue of the Technical Data Sheet for the product concerned, copies of which will be supplied on request.

Please consult our Technical Sales Department for further information

SIKA LIMITED

Watchmead, Welwyn Garden City, Hertfordshire, AL7 1BQ

Tel: 01707 394444 Email: sika@uk.sika.com

Fax: 01707 329129 www.sika.com

