

Sika® Galvashield® XP/XPT/XP2/XP4

Embedded Galvanic Anodes for Corrosion Prevention

Product Description

Sika® Galvashield® XP/XPT/XP2/XP4 embedded galvanic anodes are used in concrete rehabilitation to prevent the formation of new corrosion sites adjacent to completed patch repairs. Sika® Galvashield® XP/XPT/XP2/XP4 anodes consist of a sacrificial zinc core that is activated by the surrounding specially formulated cementitious mortar. The anode is quickly and easily fastened to the exposed reinforcing steel. Once installed, the zinc core corrodes preferentially to the surrounding rebar, thereby providing galvanic corrosion prevention to the adjacent reinforcing steel and mitigating 'Incipient Anode' formation.

Uses

- Patch repairs
- Joints between new and existing concrete
- Slab replacement
- Expansion joint repair
- Repair of epoxy-coated rebar

Characteristics / Advantages

- **Proven technology** - supported by independent test program.
- **Focused protection** - provides localized corrosion protection where it is needed the most, at the interface of the repair and the remaining contaminated concrete.
- **Economical** - low cost method of providing galvanic corrosion prevention to extend the initiation of reinforcement corrosion around patch repairs.
- **Versatile** - effective in chloride-contaminated and carbonated concrete containing chlorides. Can be used for both conventionally reinforced and prestressed or post-tensioned concrete.
- **User friendly** - installation is quick and easy, requiring no special equipment or training.
- **Low maintenance** – requires no external power source or system monitoring.
- **Measurable** – anode performance can be easily monitored if required.
- **Does not** cause hydrogen embrittlement.
- **Long lasting** – 10 to 20 year service life* reduces the need for future repairs.
- **Full System** – can be used in conjunction with Sika® FerroGard® and Sikagard® technology to offer a full corrosion management system.

* As with all galvanic protection systems, service life is dependent upon a number of factors including reinforcing steel density, concrete conductivity, chloride concentration, humidity and anode spacing

Level of Protection

Level of Protection	Description	Galvashield® XP/XPT	Galvashield® XP2/XP4
Corrosion Prevention 0.2 – 2mA/m ²	Preventing new corrosion activity from initiating	•	•
Corrosion Control 1 – 7mA/m ²	Significantly reducing or stopping on-going corrosion activity		•
Cathodic Protection 2 – 20mA/m ²	Highest level of protection intended to stop on-going corrosion activity		


Construction



Product Data

Form

Appearance



Sika® Galvashield® XP Sika® Galvashield® XPT Sika® Galvashield® XP2 XP4

Dimensions

Product Name	Anode Class	Anode Dimension (nominal)	Zinc Mass (g)
Galvashield XPT	Type AP	25 mm x 125 mm x 25 mm	60
Galvashield XP	Type AP	65 mm (dia) x 30 mm	60
Galvashield XP2	Type AC	65 mm x 80 mm x 30 mm	100
Galvashield XP4	Type AC	65 mm x 120 mm x 30 mm	160

Anode Class

First Letter Activation Method (A-Alkali)

Second Letter Application (P-Corrosion Prevention) (C-Corrosion Control)

Packaging

Galvashield® XP	20 units per box	5.2kg box
Galvashield® XPT	30 units per box	5.7kg box
Galvashield® XP2	20 units per box	5.2kg box
Galvashield® XP4	20 units per box	8.2kg box

Storage

Storage Conditions/ Shelf-Life

12 months from date of production if stored properly in original unopened, sealed and undamaged packaging in dry and cool conditions.

Design Criteria

Table 1

Anode Spacing for Low to Moderate Corrosion Risk (Chloride Content < 0.8% or Carbonated Concrete)				
Protection Level	Corrosion Prevention		Corrosion Control	
Galvashield Anode	XP or XPT	XP2	XP2	XP4
Steel Density Ratio	mm	mm	mm	mm
<0.3	750	750	600	750
0.31 – 0.6	600	700	500	700
0.61 – 0.9	500	650	400	550
0.91 – 1.2	450	550	350	450
1.21 – 1.5	400	500	250	425
1.51 – 1.8	350	450	200	375

Table 2

Anode Spacing for High Corrosion Risk (Chloride Content 0.8% to 1.5%)			
Protection Level	Corrosion Prevention		Corrosion Control
Galvashield Anode	XP or XPT	XP2	XP4
Steel Density Ratio	mm	mm	mm
<0.3	600	750	600
0.31 – 0.6	500	600	500
0.61 – 0.9	400	500	400
0.91 – 1.2	350	450	350
1.21 – 1.5	250	400	250
1.51 – 1.8	200	350	200
1.81 – 2.1	175	300	150

* Maximum spacing is based on low to moderate chlorides, typically less than 1% by wt of cement. Spacing should be reduced as appropriate for chlorides >1% and/or continuously wet substrates to extend the expected service life of the anode. Contact Sika Technical Department for advice.

Where stirrups in beams or columns are exposed, place a Sika® Galvashield® XP/XPT/XP2/XP4 anode at each stirrup location.

System Information

System Structure

Sika® Galvashield® XP is part of a Concrete Repair System in accordance with the guidelines of BS EN 1504-9

Sika® Rapid Repair Mortar: Hand Applied Mortar

Sika® MonoTop-610: Bonding primer and reinforcement coating

Sika® MonoTop-612: R4 Hand and wet spray applied repair mortar

Sika® MonoTop-615: R3 Hand and wet spray applied high build repair mortar

SikaCem® 133 Gunite R4 Dry spray applied repair mortar

Sika® MonoTop-620: Smoothing coat

Sika® FerroGard®-903: Corrosion inhibitor

Sika Embedment Mortar: Mortar for embedding Galvashield® XP/XPT/XP2/XP4

Application Details

Substrate Quality & Preparation

Concrete

Break out the concrete from around and behind the reinforcement steel in accordance with the requirements of the Product Data Sheet for the appropriate BS EN 1504-3 Classification Concrete Repair Mortar

Steel reinforcement

Rust, scale, mortar, concrete, dust and other loose and deleterious material which reduces bond or contributes to corrosion shall be removed to a minimum standard of SA2½..

Reference should also be made to BS EN1504-10:2003 for specific requirements.

Bonding Primer/ Reinforcement Coating

Bonding primer:

When a bonding primer is required apply Sika® MonoTop-610 or SikaTop® Armatec-110 EpoCem®.

Reinforcement coating:

Where a reinforcement coating is required apply Sika® MonoTop-610 or SikaTop® Armatec-110 EpoCem®.

When Sika® MonoTop-610 or SikaTop® Armatec 110 EpoCem is used as a reinforcement coating or bonding primer, do not apply within 150 mm of the tie wires or anode casing.

Application Instructions

Application Method

- The location and spacing of the anodes shall be as specified by the designer (for more information refer to Design Criteria – Table 1 & Table 2).
- Anodes are typically tied on the side or beneath the exposed reinforcement as close as practical to the edge of the surrounding concrete making sure that enough space is left to fully encapsulate the anode with the Sika Embedment Mortar.
- Minimum cover over the anodes/embedment mortar must be 20 mm or minimum thickness of the Concrete Repair Material for trafficked areas, 10 mm or minimum thickness of the Concrete Repair Material for non- trafficked areas.
- A 20mm minimum clearance on sides adjacent to repair edge should be maintained, where chloride contaminated concrete remains in contact with reinforcement place Sika® Galvashield® XP/XPT/XP2/XP4 anodes along length of reinforcement or in grid pattern at spacings recommended in Table 1 & Table 2.
- Pre-soak anode units thoroughly in clean water for a minimum of 10 minutes to a maximum of 20 minutes prior to application of the embedment mortar.
- After pre-soaking anodes use water to mix embedment mortar or concrete repair mortar. If water is to be disposed neutralise with an acid first.
- Securely fasten the anode to prepared reinforcing steel using a suitable wire twisting tool to eliminate free movement, and to ensure a good electrical connection.
- Steel continuity within the patch should be verified with an appropriate continuity meter. If discontinuous steel is present, re-establish continuity with steel tie wires.
- Following the anode installation, electrical connection between the anode tie wires and the clean reinforcing bar should be confirmed with an appropriate continuity meter. A value of between 0.1 – 1.0 Ohm shall be achieved.
- With the anodes securely in position, begin the repair process by packing the embedment mortar between the anode and the substrate to provide a conductive path to the substrate.
- Allow embedment mortar to sufficiently harden around Sika® Galvashield® XP/XPT/XP2/XP4 anode before applying concrete repair mortar.
- Complete repair with the appropriate BS EN 1504-3 Classification Concrete Repair Mortar and where applicable a cementitious bonding primer.

Notes on Application / Limitations

Sika® Galvashield® XP/XPT/XP2/XP4 anodes are not suitable for use with epoxy and polyester repair mortars or bonding primers, as these are non conductive

Sika® Galvashield® XP/XPT/XP2/XP4 anodes are not intended to address or repair structural damage. Where structural damage exists, consult a structural engineer.

Sika® Galvashield® XP/XPT/XP2/XP4 anodes are designed to provide localized galvanic corrosion prevention. To provide galvanic corrosion control over a broader area, Sika® Galvashield® XP/XPT/XP2/XP4 anodes can be used in conjunction with Sika® Galvashield® CC anodes placed in a grid pattern in the remaining sound but contaminated concrete. For more information on corrosion mitigation strategies, contact Sika Technical Department.

Caution should be exercised when selecting corrosion mitigation systems for post-tensioned, pre-stressed or otherwise highly stressed steel.

Value Base All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

Local Restrictions Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

Health and Safety Information For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

Legal Notes The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Galvashield, Vector and the Vector logo are registered trademarks of Vector Corrosion Technologies Ltd.
Patents: US 6022469, 6303017, 6193857 © 2009 Vector Corrosion Technologies



Sika Limited
Watchmead
Welwyn Garden City
Hertfordshire
AL7 1BQ
United Kingdom
Phone +44 1707 394444
Telefax +44 1707 329129
www.sika.co.uk
email: sales@uk.sika.com



Certificate No. EMS 4308



Certificate No. FM 12504