

Sikadur®-31 EF

2-part thixotropic multipurpose epoxy adhesive

Product Description

Sikadur®-31 EF is a moisture tolerant, thixotropic, structural two part adhesive and repair mortar, based on a combination of epoxy resins and special fillers, designed for use at temperatures between +10°C and +30°C.

Uses

As a structural adhesive and mortar for:

- Concrete elements
- Hard natural stone
- Ceramics, fibre cement
- Mortar, Bricks, Masonry
- Steel, Iron
- Wood
- Polyester, Epoxy

As a repair mortar and adhesive:

- Corners and edges
- Holes and void filling
- Vertical and overhead use

Joint filling and crack sealing:

- Joint and crack arris / edge repair

Characteristics / Advantages

Sikadur®-31 EF has the following advantages:

- Easy to mix and apply
- Good adhesion to most construction materials
- Thixotropic: non-sag in vertical and overhead applications
- Hardens without shrinkage
- Different coloured components (for mixing control)
- No primer needed
- Abrasion resistant
- Impermeable to liquids and water vapour
- Chemical resistant

Approval / Standards

Complies to the requirements of EN 1504-4:2005

Product Data

Form

Colours	Part A:	light grey
	Part B:	dark grey
	Parts A+B mixed:	concrete grey

Packaging	1.2 kg (A+B) Pre-batched unit
	6 kg (A+B) Pre-batched unit

Storage

Storage Conditions / Shelf Life	12 months from date of production if stored properly in original unopened, sealed and undamaged packaging, in dry conditions at temperatures between +5°C and +30°C. Protect from direct sunshine.
--	--

Technical Data

Chemical Base	Epoxy resin.
Density	~1.7 ± 0.1 kg/l (part A+B mixed) (at +23°C)
Sag Flow	On vertical surfaces it is non-sag up to 10 mm thickness. (According to EN 1799)
Layer Thickness	30 mm max. When using multiple units, one after the other. Do not mix the following unit until the previous one has been used in order to avoid a reduction in handling time.
Change of Volume	Shrinkage: Hardens without shrinkage.
Thermal Expansion Coefficient	Coefficient W: 4.6 x 10 ⁻⁵ per °C (Temp. range -20°C - +40°C) (According EN 1770)
Thermal Stability	Heat Deflection Temperature (HDT): HDT = +53°C (7 days / +23°C) (According to ASTM D 648)

Mechanical / Physical Properties

Compressive Strength

(According to ASTM D 695)

Curing time	Curing temperature		
	+10°C	+23°C	+30°C
1 day	~15 N/mm ²	~29 N/mm ²	~34 N/mm ²
3 days	~30 N/mm ²	~39 N/mm ²	~46 N/mm ²
7 days	~38 N/mm ²	~47 N/mm ²	~51 N/mm ²
14 days	~45 N/mm ²	~53 N/mm ²	~55 N/mm ²

Flexural Strength

(According to DIN EN 53452)

Curing time	Curing temperature		
	+10°C	+23°C	+30°C
1 day	~6 N/mm ²	~10 N/mm ²	~20 N/mm ²
3 days	~20 N/mm ²	~21 N/mm ²	~26 N/mm ²
7 days	~25 N/mm ²	~28 N/mm ²	~29 N/mm ²
14 days	~30 N/mm ²	~32 N/mm ²	~30 N/mm ²

Tensile Strength

(According to ISO 527)

Curing time	Curing temperature		
	+10°C	+23°C	+30°C
1 day	~7 N/mm ²	~10 N/mm ²	~11 N/mm ²
3 days	~18 N/mm ²	~20 N/mm ²	~24 N/mm ²
7 days	~21 N/mm ²	~22 N/mm ²	~25 N/mm ²
14 days	~24 N/mm ²	~24 N/mm ²	~29 N/mm ²

Bond Strength

(According to EN ISO 4624, EN 1542 and EN 12188)

Time	Temperature	Substrate	Bond strength
1 day	+10°C	Concrete dry	> 3 N/mm ² *
1 day	+10°C	Concrete moist	> 3 N/mm ² *
7 days	+25°C	Steel	~ 18 N/mm ²

*100% concrete failure.

E-Modulus

Compressive:
~ 6'500 N/mm² (14 days at +23°C) (According to ASTM D695)

Flexural:
~ 7'700 N/mm² (14 days at +23°C) (According to EN 53452)

Tensile:
~ 6'900 N/mm² (14 days at +23°C) (According to ISO 527)

Elongation at Break

0.3 ± 0.1% (7days at +23°C) (According to ISO 527)

System Information

Application Details


Consumption / Dosage	The consumption of Sikadur®-31 EF is ~ 1.7 kg/m ² per mm of thickness.
Substrate Quality	<p>Mortar and concrete must be older than 28 (depends on minimal requirement of strengths).</p> <p>Verify the substrate strength (concrete, masonry, natural stone).</p> <p>The substrate surface (all types) must be clean, dry or mat damp (no standing water) and free from contaminants such as dirt, oil, grease, existing surface treatments and coatings etc..</p> <p>Steel substrates must be de-rusted similar to Sa 2.5.</p> <p>The substrate must be sound and all loose particles must be removed.</p>

Substrate Preparation	<p>Concrete, mortar, stone, bricks: Substrates must be sound, dry or mat damp (no standing water), clean and free from laitance, ice, standing water, grease, oils, old surface treatments or coatings and all loose or friable particles must be removed to achieve a laitance and contaminant free, open textured surface.</p> <p>Steel: Must be cleaned and prepared thoroughly to an acceptable quality i.e. by blast cleaning and vacuum. Avoid dew point conditions.</p>
------------------------------	--

Application Conditions / Limitations

Substrate Temperature	+10°C min. / +30°C max.
Ambient Temperature	+10°C min. / +30°C max.
Material Temperature	Sikadur®-31 EF must be applied at temperatures between +10°C and +30°C
Substrate Moisture Content	<p>Substrate must be dry or mat damp (no standing water)</p> <p>Brush the adhesive well into the substrate</p>
Dew Point	<p>Beware of condensation!</p> <p>Substrate temperature during application must be at least 3°C above dew point.</p>

Application Instructions

Mixing	Part A : part B = 3 : 1 by weight or volume
Mixing Time	 <p>Pre-batched units: Mix parts A+B together for at least 3 minutes with a mixing spindle attached to a slow speed electric drill (approx. 300 rpm) until the material becomes smooth in consistency and a uniform grey colour. Avoid aeration while mixing. Then, pour the whole mix into a clean container and stir again for approx. 1 more minute at low speed to keep air entrapment at a minimum. Mix only that quantity which can be used within its potlife.</p>

Application Method / Tools	<p>When using a thin layer adhesive, apply the mixed adhesive to the prepared surface with a spatula, trowel, notched trowel, (or with hands protected by gloves).</p> <p>When applying as a repair mortar, use some formwork.</p> <p>When using for bonding metal profiles onto vertical surfaces, support and press uniformly using props for at least 12 hours, depending on the thickness applied (not more than 5 mm) and the room temperature.</p> <p>Once hardened check the adhesion by tapping with a hammer.</p>
-----------------------------------	--

Cleaning of Tools Clean all tools and application equipment with Sika® Thinner C immediately after use. Hardened / cured material can only be mechanically removed.

Potlife Potlife (200 g) adiabatic (According to EN ISO 9514)

+10°C	+23°C	35°C	+40°C
~ 120 minutes	~ 80 minutes	~ 42 minutes	~ 30 minutes

The potlife begins when the resin and hardener are mixed. It is shorter at high temperatures and longer at low temperatures. The greater the quantity mixed, the shorter the potlife. To obtain longer workability at high temperatures, the mixed adhesive may be divided into portions. Another method is to chill parts A+B before mixing them (not below +5°C).

Value Base All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

Local Restrictions Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

Health and Safety Information For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

Legal Notes The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.



SIKA LIMITED

Head Office · Watchmead · Welwyn Garden City · Hertfordshire · AL7 1BQ · United Kingdom
Phone: +44 1 707 394444 · Fax: +44 1 707 329129 · www.sika.co.uk

