

# Sikafloor®-ProSeal

## Curing and sealing compound for concrete floors

### Product Description

Sikafloor- ProSeal® is a solvent based, clear acrylic resin polymer solution used to cure, harden and seal fresh or hardened concrete.

### Uses

- Sikafloor®-ProSeal is used for optimum curing and sealing of fresh concrete floors and structures
- Curing compound in order to limit surface drying and cracking
- Provides curing and sealing for Sikafloor® dry shake hardeners
- Anti-dust treatment and improvement of the abrasion resistance of existing concrete surfaces
- Suitable for exterior and interior application

### Characteristics / Advantages

- Excellent moisture retention
- Good adhesion to old and new concrete
- Quick drying
- Helps control dusting for both new and existing concrete floor surfaces
- Effectively cures and seals concrete surfaces in a single, economic operation
- Non yellowing
- Easy application by spray or roller

### Tests

#### Approval / Standards

Tested for water retention according to ASTM C-156 for curing liquids type 1, class  
Conforms to the requirements of EN 13813 SR - B 1.5.  
Epoxy textured roller and seal coat according to EN 13813:2002, DoP 01 08 03 04 005 0 000004 1049 and provided with the CE-mark

### Product Data

#### Form

**Appearance / Colours** Clear Liquid

**Packaging** 25 l metal pails and 200 l metal drums.



---

## Storage

---

**Storage Conditions / Shelf Life** 12 months from date of production, if stored properly in original, unopened and undamaged sealed containers, in dry conditions at temperatures between +5°C and +25°C. Protect from frost.

---

## Technical Data

---

**Chemical Base** Solvent based acrylic resin.

---

**Density** ~ 0.9 kg/l (at +20°C)

---

### Curing Efficiency

(ASTM C - 156)

	Loss of water (g / 100 cm <sup>2</sup> )	Loss of water compared to ASTM C309 (100% = 5.5 g/100 cm <sup>2</sup> )	Loss of water compared to untreated concrete (100% = 18.7 g/100 cm <sup>2</sup> )
Sikafloor®-ProSeal	4.8	87%	25%
		<b>Efficiency</b>	<b>75%</b>

---

**Chemical Resistance** The product is not intended for chemical exposure.

---

## System Information

---

**System Structure** All applications 1 - 2 coats.

---

### Application Details

---

**Consumption / Dosage** 0.1 - 0.25 l/m<sup>2</sup>/coat. (4 - 10 m<sup>2</sup>/l/coat)

This figure is theoretical and does not include for any additional material required due to surface porosity, surface profile, variations in level and wastage, etc.

---

### Substrate Quality

*Fresh concrete:*

Surface must be free of bleed water and of sufficient strength to withstand finishing operations.

*Hardened / old concrete:*

The substrate must be prepared by suitable mechanical preparation techniques such as high-pressure water jetting or abrasive blastcleaning.

All dust, loose and friable material must be completely removed from all surfaces before application of the product, preferably by brush and/or vacuum.

If in doubt apply a test area first.

---

### Substrate Preparation

*Fresh concrete:*

The concrete must be prepared by suitable power or manual floating / tamping techniques.

*Hardened / old concrete:*

The substrate must be prepared by suitable mechanical preparation techniques such as high-pressure water or abrasive blast cleaning equipment.

All dust, loose and friable material must be completely removed from all surfaces before application of the product, preferably by brush and/or vacuum.

---

## Application Conditions / Limitations

**Substrate Temperature** +10°C min. / +30°C max.

**Ambient Temperature** +10°C min. / +30°C max.

**Relative Air Humidity** 80% r.h. max.

**Dew Point** Beware of condensation!

The substrate and uncured floor must be at least 3°C above dew point to reduce the risk of condensation or blooming on the floor finish.

## Application Instructions

**Mixing** Sikafloor®-ProSeal is supplied ready for use. Stir thoroughly before use.

**Mixing Time** 2 minutes.

**Mixing Tools** Electric stirrer with low speed (~ 300 rpm).

**Application Method / Tools** For fresh concrete, apply immediately after finishing techniques have been completed.

Apply in a continuous even film by low-pressure spray unit. The suitability of spraying equipment must be confirmed by trials.

Application also possible by brush or roller.

To achieve the highest visual aesthetics and performance, a second coat is recommended.

Wait for first coat to dry tack free before applying a second coat.

**Cleaning of Tools** Clean all tools and application equipment with Sika® Thinner C immediately after use. Hardened / cured material can only be removed mechanically.

**Waiting Time / Overcoating** Allow previous coats to become tack free before applying additional coats.

Substrate temperature	+10°C	+20°C	+30°C
Time	~ 60 minutes	~ 25 minutes	~ 20 minutes

Times are approximate and will be affected by changing substrate and ambient conditions, particularly temperature and relative humidity.

## Notes on Application / Limitations

In hot weather (above +25°C) store Sikafloor®-ProSeal in a cool place prior to use.

In low temperatures (below +10°C) the product may thicken and be difficult to spray.

Do not use sprayers, which have been used to spray silicones or release agents.

Do not mix differing formulations of Sika® or other curing membranes.

Ensure spraying equipment is cleaned thoroughly before use and residues of previous membranes are removed.

Sikafloor®-ProSeal must be removed prior to the application of a coating system.

Sikafloor®-ProSeal increases abrasion resistance compared to C25 concrete, but will gradually de-grade and be removed by environmental exposure conditions and trafficking.

## Curing Details

### Applied Product ready for use

Substrate temperature	+10°C	+20°C	+30°C
Foot traffic	~ 4 hours	~ 3 hours	~ 2 hours
Full cure	~ 24 hours	~ 20 hours	~ 16 hours

Note: Times are approximate and will be affected by changing ambient and substrate conditions.

## Cleaning / Maintenance

### Methods

To maintain the appearance of the floor after application, Sikafloor®-ProSeal® must have all spillages removed immediately and must be regularly cleaned using rotary brushes, mechanical scrubbers, scrubber dryers, high pressure washers, wash and vacuum techniques, etc., using suitable detergents and waxes.

### Value Base

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

### Local Restrictions

Please note that as a result of specific local regulations the performance of this product may vary from country to country. Please consult the local Product Data Sheet for the exact description of the application fields.

### Health and Safety Information

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

### Legal Notes

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.



### SIKA LIMITED

Head Office · Watchmead · Welwyn Garden City · Hertfordshire · AL7 1BQ · United Kingdom  
 Phone: +44 1 707 394444 · Fax: +44 1 707 329129 · www.sika.co.uk

